



TECSOUND® 2FT80

TECSOUND 2FT is a soundproofing complex made up of the polymer-based, asphalt-free Tecsound synthetic membrane sandwiched between two porous felt mats, both formed in such a way as to offer excellent acoustic insulation in different building elements: walls, ceilings, roofs, etc.

PROPERTIES

- High acoustic insulation, combined with soft, flexible elements (plasterboard, wood, conglomerate).
- Flexible.
- Easy to handle and adaptable to uneven surfaces.
- Easy to cut with a knife or scissors
- Cold- and heat-resistance.
- Excellent ageing resistance
- Rotproof.

USES

Soundproofing of horizontal (ceilings) and vertical enclosures, where excellent soundproofing against airborne noise is required.

- Specially recommended in partition walls.
- Soundproofing against airborne noise in vertical surfaces.
- Soundproofing against airborne noise in ceilings.
- Reduction of impact noise level in all types of floors, applied underneath the flooring.

Its main applications cover new jobs and refurbishing work, industry, cinemas, theatres, sports complexes, discos, bars, restaurants, hotels, shopping centres, etc.

For further information see examples in systems sheets.

TECHNICAL DATA

Test	Value
Density	2.0 g/cm ³ ± 0.05
Pliability (UEAtc)	Does not break with bending at -20°C
Tensile strength (UNE 104-281/6.6)	> 30 N/cm ² (Tecsound membrane)
Elongation (UNE 104-281/6.6)	300 % (Tecsound membrane)
Compressive strength	4.84 Kg/cm ²
Thermal conductivity coefficient	0.037 W/m°C (felt)
Weight of porous felt	600 g/m ²
Soundproofing properties	See systems sheet

INSTRUCTIONS FOR USE

Substrate: TECSOUND® lends itself to all types of normal building substrates (renderings, gypsum board, metal, DM, plastic materials). The substrate must be even, smooth, clean and dry. It must also be free from elements that could damage the membrane. If the rendering is old, its condition must be checked to avoid adherence problems of the TECSOUND 2FT o the rendering.

Installation of the membrane: prior to installing the membrane, contact adhesive must be applied to both substrate and soundproofing complex, and left to dry according to the instructions of the adhesive manufacturer before bonding the two surfaces. Pressure must be exerted on all the points



to ensure correct adherence.

The product could be installed mechanically fastened. The number of fixings is 5 units/m². Fasteners made of plastic or pvc must be used.

Laps: Overlap 5 cm. both vertically and horizontally. Care must be taken to always seal the laps correctly, as small openings can reduce the level of acoustic insulation required. In case of installing the product butt joint then Tecsound S Band 50 must be used to seal the joint.

PACKAGING AND STORAGE

Tipo	Kg/m²	Thickness (mm.)	Packaging	Rolls per pallet
Tecsound® 2FT80	8,2	27,5	5,5 m. x 1,20 m rolls	6 rolls (39,6 m ²)

The product must be stored in dry premises, protected against weathering, and must not be exposed to temperatures exceeding 35°C for long time. Maximum recommended storage time is one year.

TEXSA, S.A. reserves the right to modify the data herein without previous notice and refuses all responsibility in the event of irregularities caused by incorrect use of the product. Values reflected in the technical data sheet correspond to average values obtained from tests carried out in our laboratory.